

DESIGNATION	ALLOY GROUP	ZINC	ZINC	ZINC	ZINC	ZINC-ALUMINUM	ACuZinc	MAGNESIUM	ALUMINUM	PLASTIC	BRASS	POWDERED METAL	MILD STEEL		
	ASTM Designation	AC43A	AG40A	AC41A	AG40B						B16	B 426 grade 1	C1010		
	General Designation	ZAMAK 2	ZAMAK 3	ZAMAK 5	ZAMAK 7	ZA-8	ACuZinc 5	AZ-91D	380	Polypropylene	Nylon (30% Glass)	Brass 360	FC-0208-R as sintered	1010	
COMPOSITION PERCENTAGE BY WEIGHT	Al Aluminum	3.5 - 4.3	3.5 - 4.3	3.5-4.3	3.5 - 4.3	8.0 - 8.8	2.5 - 3.3	8.3 - 9.7	—	—	—	—	—	—	
	Cu Copper	2.5 - 3.0	0.25 Max.	0.75 - 1.25	0.25 Max.	0.8 - 1.3	5.0 - 6.0	0.03 Max.	—	—	—	—	—	—	
	Mg Magnesium	0.02 - 0.05	0.02 - 0.05	0.03 - 0.08	0.005 - 0.02	0.015 - 0.030	0.025 - 0.05	Remainder	—	—	—	—	—	—	
	Fe Iron (Maximum)	0.100	0.100	0.100	0.075	0.075	0.075	0.005	—	—	—	—	—	—	
	Pb Lead (Maximum)	0.005	0.005	0.005	0.003	0.006	0.005	0.02	—	—	—	—	—	—	
	Cd Cadmium (Maximum)	0.004	0.004	0.004	0.002	0.006	0.004	0.02	—	—	—	—	—	—	
	Sn Tin (Maximum)	0.003	0.003	0.003	0.001	0.003	0.003	0.02	—	—	—	—	—	—	
	Ni Nickel	—	—	—	0.005 - 0.020	—	—	—	0.002 Max.	—	—	—	—	—	—
	Zn Zinc	Remainder	Remainder	Remainder	Remainder	Remainder	Remainder	0.35 - 1.0	—	—	—	—	—	—	
	PHYSICAL PROPERTIES	Density													
kg/m ³		6655	6600	6700	6600	6300	6850	1827	2713	900	1400	8500	6700	7900	
lb/in ³		0.240	0.238	0.242	0.24	0.227	0.247	0.066	0.098	0.032	0.05	0.307	0.242	0.283	
Melting Range															
°C		379 - 390	381 - 387	380 - 386	381 - 387	375 - 404	402 - 502	468 - 596	538 - 593	—	—	885 - 900	N/A	1370	
°F		715 - 734	718 - 728	717 - 727	718 - 728	707 - 759	755 - 936	875 - 1105	1000 - 1100	—	—	1630 - 1660	N/A	2500	
Coefficient of Thermal Expansion															
µm/m°K		27.8	27.4	27.4	27.4	23.3	24.1	25.2	21.2	80 - 150	23 - 40	20.5	9.2	11.4	
µin/in°F		15.4	15.2	15.2	15.2	12.9	13.3	14.0	11.8	44 - 83	13 - 22	11.4	5.1	6.3	
Thermal Conductivity															
W/m°K		104.7	113.0	108.9	113.0	114.7	106.0	72.3	96.2	0.16 - 0.24	0.5	115.0	44 (est.)	49.8	
BTU/ft.hr.°F		60.5	65.3	62.9	65.3	66.3	61.2	41.8	55.6	0.092 - 0.139	0.29	67.0	25 (est.)	28.8	
Electrical Conductivity															
10 ⁻⁹ Ohm. m		68.4	63.9	66.3	63.9	62.2	64.0	141.0	63.9	N/A	N/A	66.0	N/A	143	
%IACS		25.0	27.0	26.0	27.0	27.7	26.9	12.2	27.0	N/A	N/A	26.0	N/A	12.1	
MECHANICAL PROPERTIES	Tensile Strength														
	MPa	359	283	328	283	374	407	234	324	33	120	379 - 470	415	365	
	psi	52,000	41,000	47,600	41,000	54,200	59,000	34,000	47,000	4,800	17,400	55,000 - 68,000	60,000	52,900	
	Yield Strength (0.2% offset)														
	MPa	283	221	228	221	290	338	159	165	—	—	305 - 360	330	305	
	psi	41,000	32,000	33,000	32,000	42,000	49,000	23,000	24,000	—	—	44,000 - 52,000	48,000	44,200	
	Compressive Yield Strength (0.1% offset)														
	MPa	641	414	600	414	252	N/A	165	N/A	—	—	N/A	N/A	N/A	
	psi	93,000	60,000	87,000	60,000	37,000	N/A	24,000	N/A	—	—	N/A	N/A	N/A	
	Elongation (% in 2 inches) (% in 51 mm)														
		7	10	7	13	8	5	3	3	>100	6	18 - 53	1	18	
	Shear Strength														
	MPa	317	214	262	214	276	280	138	186	—	—	220 - 260	N/A	311	
	psi	46,000	31,000	38,000	31,000	40,000	40,600	20,000	27,000	—	—	32,000 - 38,000	N/A	45,000	
	Hardness														
BHN (Brinell)	up to 100	up to 82	up to 91	up to 80	up to 103	up to 115	up to 63	up to 80	—	—	120	110	124 - 162		
Impact Strength															
J	47.5 ¹	58.3 ¹	65.1 ¹	58.3 ¹	42.0 ¹	N/A	6.0 ¹	4.0 ²	—	—	N/A	6.8	N/A		
ft. lbs.	35 ¹	43 ¹	48 ¹	43 ¹	31 ¹	N/A	5 ¹	3 ²	—	—	N/A	5	N/A		
Fatigue Strength (Rotary Bend 5x10⁶ cycles)															
MPa	58.6	47.6	56.5	46.9	103	N/A	97	138	13.8	17.2	138.0	155.0	N/A		
psi	8,500	6,900	8,200	6,800	15,000	N/A	14,000	20,000	2,000	2,500	20,000	23,000	N/A		

Note: Data shown is typical for the material and process used and is intended for comparison and guidance only.
 Note: FisherCast die casts components in these alloys.

¹ 1/4 inch Unnotched Charpy ² 10mm Unnotched Charpy

North American Operations

710 Neal Drive
 Peterborough, ON Canada K9J 6X7

Tel: (705) 748-9522
 Fax: (705) 748-6763
 Toll Free (U.S./Canada): 1 (866) 536-CAST (2278)
 E-mail: info@fishercast.com

European Operations

1 Fisher Road, Offa's Dyke Business Park
 Welshpool, Powys, Wales
 United Kingdom SY21 8JF

Tel: +44 1938 55 55 00
 Fax: +44 1938 55 60 56
 E-mail: info@fishercast.com

Call us for assistance
 with your small component
 design challenges.

www.fishercast.com



ACuZinc® is a registered trademark of General Motors Corp.

